




# PITTSBURGH METAL ROOF COLORS


24 gauge for use on Pittsburgh All-Steel Shelters  
Multi-Rib Profile Standard (available in Standing Seam at an upcharge)




\* Regal White




\* Surrey Beige



Light Stone




\* Ash Gray




\* Charcoal



Matte Black



▲ Roman Blue




\* Patina Green



\* Evergreen



Patrician Bronze



Autumn Red




Litchfield Teal



Tudor Brown




\* Galvalume Plus



Copper




\* Brandywine



\* Regal Blue

Optional Standing Seam



24GA. MEDALLION-LOK PROFILE



Hartford Green



\* Brite Red

\* Denotes availability in Standing Seam.

▲ Denotes master coil in inventory.

Allow extra time for slitting. Set-up charges may apply.

NOTE: Inventory and color offerings can change without notice.

Select a metal roof finish above or provide us with an RAL # to create a custom color (at an upcharge).

- Actual steel frame and metal roof colors may vary slightly.
- Before you place an order, please request an actual color sample from Litchfield.
- Litch-Kicker standard frame finish features a 10 year warranty.
- Multi & Max Rib metal roof panels feature a 30 year warranty except Brite Red (10 years).
- Standing Seam metal roof panels feature a 20 year warranty except Brite Red (10 years).

## Other Available Metal Roof Profiles

Multi-Cor	
Multi-V	
Mega-Rib	
Mini-Rib	
Mac-Rib	

NOTE: All of the roof profiles shown are not available in every color. Certain panels must utilize a wood substructure. Please check with the factory or your local Litchfield Sales Representative for assistance with your roof panel selection. Additional charges may apply to these metal roof profiles.

## Metal Roof Specifications

Description	Test Method	Galvalume Substrate with Fluoropon Coating
Accelerated Weathering	ASTM G 23	Hours 2000 - Chalk Rating 8 - Color 2 Δ E Max.
Salt Spray	ASTM B 117	Hours 1000 - Scribe Rating 7 1/16" Field Rating 10 - No Blisters
Humidity	ASTM D 2247	Hours 2000 - Field Rating 10 - No Blisters
Formability	ASTM D 522	1/8" Mandrel - No Cracking - No loss of Adhesion
Adhesion	ASTM D 3359	No Loss of Adhesion
Pencil Hardness	ASTM D 3363	HB Minimum
Specular Gloss	ASTM D 523	30 or Less @ 60°
Impact Resistance	ASTM D 2794	3X Metal Thickness in inch-lb - No loss of Adhesion
Abrasion Resistance	ASTM D 968	Total Sands = 80 liters
Acid Resistance	ASTM D 1308 (Procedure 6.2) (Independent of Substrate)	10% Hydrochloric Acid 24 Hours - No visible change 20% Hydrochloric Acid 18 Hours - No visible change 20% Sulfuric Acid 18 Hours - No visible change 25% Sodium Hydroxide 1 Hour - No visible change 20% Muriatic Acid 15 Minutes - No visible change
Flame Test	ASTM E 84	Class A Coating

Litchfield Landscape Elements features a Kynar 500® coating on all of its metal roof systems. Kynar 500® coatings are proven to provide unsurpassed protection against panel chalk and fade.

Fluoropon® is a registered trademark of the Valspar Corporation.